

AVERAGE PELLET COUNT FOR SHOTSHELLS

TUNGSTEN-IRON				
Weight of Shot in Ounces (Grams)				
Shot Size	7/8 (24.80)	1 (28.35)	11/8 (31.89)	13/8 (38.98)
4	122	140	157	192
2	82	94	106	129
BB		54	60	74

TUNGSTEN-POLYMER				
Weight of Shot in Ounces (Grams)				
Shot Size	1 (28.35)	11/8 (31.89)	11/4 (35.44)	13/8 (38.98)
6	255	253	281	309
4	135	152	169	186

STEEL Weight of Shot in Ounces (Grams)									
Shot Size	3/4 (21.5)	15/16 (26.58)	1 (28.35)	11/8 (31.89)	11/4 (35.44)	13/8 (38.98)	11/2 (42.52)	19/16 (44.30)	15/8 (46.06)
7	316	395	422	475	527	580	633	659	685
6	236	295	315	354	394	433	472	492	512
5	182	228	243	273	304	334	364	380	395
4	144	180	192	216	240	264	288	300	312
3	118	143	158	178	197	217	237	247	257
2	94	117	125	141	156	172	187	195	203
1	77	97	103	116	129	142	154	161	167
BB	54	67	72	81	90	99	108	112	117
BBB	46	58	62	70	77	85	93	97	101
T	39	49	52	58	65	71	78	81	84
F	30	37	40	45	50	55	60	62	65

LEAD Weight of Shot in Ounces (Grams) (3% ANTIMONY)													
Shot Size	1/2 (14.17)	11/16 (19.49)	3/4 (21.25)	7/8 (24.80)	1 (28.35)	11/8 (31.89)	11/4 (35.44)	13/8 (38.98)	11/2 (42.52)	15/8 (46.06)	17/8 (53.15)	2 (56.70)	2 1/4 (63.78)
9	292	402	439	512	585	658	731	804	877	951	1097	1170	1316
8½	249	342	373	435	497	559	621	683	745	808	932	994	1118
8	205	282	307	359	410	461	512	564	615	666	769	820	922
7½	175	241	262	306	350	394	437	481	525	569	656	700	787
6	112	155	169	197	225	253	281	309	337	366	422	450	506